




Detector Loop Sealant

5000



**Loop sealant
designed specifically
for the job**



3M™ Detector Loop Sealant... easy to use...superior protection

3M detector loop sealant encapsulates, insulates and protects the wires of a detector loop from the effects of the harsh roadway environment. In temperature extremes, it retains flexibility so the wires are continuously protected to prevent loop failure.

Some good reasons you should be using 3M detector loop sealant:

Saves application time

3M loop sealant is ready to use. There is no need to measure, mix or heat and no smoothing is required. Sealant can be applied on crowned or sloped roadways. It will not run to low spots.

Outstanding protection

Loop wires are held in position and completely contained in a tough, yet flexible, rubber cocoon. Wires are protected against movement, road debris penetration and moisture, eliminating these causes of false calls.

Reduced maintenance

3M sealant will not shrink, so call-backs for refilling are eliminated. And sharp objects will not penetrate the tough rubber. Sealant cures with smooth surface so there is no need for finishing.

Natural curing

Sealant reacts with moisture in the environment to produce a rubber that is resistant to weather, oils, gasoline, antifreeze, brake fluid and road salt.

Long lasting

The sealant will not become brittle with age or temperature extremes.

Temperature stable

The sealant won't degrade in high temperatures or fracture at temperatures as low as -40°F.

Roadway compatibility

3M sealant can be used with either concrete or asphalt, fresh or aged, wet or dry surfaces.

Fast, complete application

3M supplies special nozzles that help you fill the sawcut from the bottom to the top.

New, more convenient application

3M's new ply pack is especially well suited for customers who use applicator guns to apply sealant. Dispensing rate is improved by up to 300%. Disposable packaging waste is reduced by over 90% at the work site.



Applicator gun and
ply pack packaging

Simple, fast and sure way to do the job right

Specifications

(Performance Properties*)

Cured Sealant

Hardness (Indentation)

Rex Type A

Model 1700. 75

Tensile Strength. 800 psi (56.24 kg/cm²)

Elongation 400%

Weathering Resistance

XW-Weatherometer

(350 hours) Slight chalking

Salt Spray Resistance

[28 days @ 100°F (38°C)

5% NaCl] No significant
change in tensile
strength and
elongation

ARC Resistance 71 seconds

Dielectric Constant 6.35 @ 50Hz
4.33 @ 500,000 Hz

Wet Sealant

Weight 10.0 lbs./gal. (1.258 kg/L)

Non Volatile Content

(by Weight) 80%

Viscosity Brookfield RVF #6

Spindle @ 20 RPM

80°F (27°C) 30,000 cps

Tack Free Time


(Polyethylene Film) 24 hours

Flash Point. 109°F (43°C)

* All results based on 3M laboratory testing.



1. Cut the loop.



2. Flush out debris and blow out standing water.



3. Install loop wires.



4. Fill sawcut with 3M[®] Detector Loop Sealant.

Important Notice to Purchaser:

THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. 3M shall replace or refund the purchase price of such quantity of product found to be defective in material or manufacture or not in conformance with 3M's written specifications. Except as herein provided, 3M shall not be liable in contract or in tort for any injury, loss or damage, whether direct, indirect, incidental, special or consequential, arising out of the use, misuse, or the inability to use the product for intended use. No statement of recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.



**Intelligent Transportation Systems
3M Safety and Security Systems Division**

3M Center Building 225-4N-14
St. Paul, MN 55144-1000
1-800-328-7098
1-800-224-2085 FAX
612-575-5794
612-737-1055 FAX
<http://www.mmm.com/its>

3M Canada Company

P.O. Box 5757
London, Ontario, Canada
N6A 4T1
1-800-3MHELPS



50% pre-consumer waste paper
10% post-consumer waste paper

Printed in USA
©3M, August 1997

75-0500-2244-3